

toner plastics

Technical Data Sheet

PETG

Effective Date: 01/05/2022

Revision Number: 02

<i>Filament Specifications</i>	<i>Typical Value</i>	<i>Unit</i>
Nominal Outer Diameter	1.75 / 2.88	mm
OD Tolerance	± 0.05	mm
Ovality	< 0.05	mm

<i>Physical Properties</i>	<i>Standard</i>	<i>Unit</i>	<i>Typical Value</i>
Density	ISO 1183	g/cc	1.29

<i>Mechanical Properties</i>	<i>Standard</i>	<i>Unit</i>	<i>Typical Value</i>
Tensile Strength, Break	ISO 527	MPa	49
Tensile Elongation, Break	ISO 527	%	9.2
Tensile Modulus	ISO 527	MPa	800
Flexural Modulus	ISO 178	MPa	1600
Flexural Strength	ISO 178	MPa	17

<i>Thermal Properties</i>	<i>Standard</i>	<i>Unit</i>	<i>Typical Value</i>
Glass Transition Temperature (T _g)	DSC	°C	80
Heat Deflection Temperature (HDT)	ISO 75	°C (@ 0.45 MPa)	70

<i>Electrical Properties</i>	<i>Standard</i>	<i>Unit</i>	<i>Typical Value</i>
Surface Resistivity	ASTM D257	Ω/sq	> 10 ¹²

Disclaimer: The technical data contained on this data sheet is furnished without charge or obligation and accepted at the recipient's sole risk. This data should not be used to establish specifications limits or used alone as the basis of design. The data provided is not intended to substitute any testing that may be required to determine fitness for any specific use.